

RUST-OLEUM®

8100 SYSTEM OVERKRETE® XTRA S

PREMIUM 100% SOLIDS EPOXY FLOOR COATING - SMOOTH

DESCRIPTION AND USES

OverKrete® Xtra S is a floor coating system applied at a thickness of 16 to 50 mils. It is designed for use in mild to moderate chemical environments and can tolerate constant rubber wheel traffic. This coating can be used in various ways, a 45-50 mil anti-skid textured surface, a 16 mil smooth finish.

This premium formulation provides improved color and gloss retention over standard epoxy floor coatings.

For vertical surfaces, use OverKrete® V.

PRODUCT FEATURES AND BENEFITS

CORROSION RESISTANCE

OverKrete Xtra S is resistant to a wide range of chemicals. Due to the thinness of this coating, it is not recommended for continuous or prolonged exposure to chemicals. For more detailed chemical resistance information, refer to the Heavy-Duty Concrete Flooring Solutions Guide.

This coating complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities. This coating is impervious to moisture and easily cleaned and sanitized.

PRODUCTS

8100 System OverKrete S is available in twelve standard colors. Custom colors are available upon request. Refer to the Rust-Oleum color chart. Product codes listed below are 3-Gallon Kits. Mixing ratios are shown on the product labels.

SKU	DESCRIPTION
237466	Natural
237477	National Blue
237481	Light Green
237485	Safety Yellow
237489	Tile Red
237494	Black
237499	Dunes Tan
237504	Dark Gray
237509	Light Gray
237522	Navy Gray
237526	White
237518	Super Light Gray
237473	Clear
237530	Custom

TYPICAL USES

OverKrete Xtra S coating is used where one or more of the following properties are required:

- Splash and spill corrosion resistance
- High abrasion resistance
- Anti-skid safety surfaces (when used in conjunction with a broadcasted aggregate)
- Easy to clean and maintain
- Aesthetically pleasing surfaces

It may be used directly over concrete, or as a topcoat for other Rust-Oleum floor toppings.

TYPICAL APPLICATIONS

Walkways
 Light warehousing & storage areas
 Light manufacturing
 Permanent marker lines/parking lots
 Show rooms/clean rooms
 Boiler plants/laboratories
 Animal treatment areas
 Electronics industry
 Automotive assembly/showrooms
 Airport baggage handling and ramps
 Wineries and breweries
 Bottling/beverage industries
 Chemical/meat packing/poultry plants/dairies
 Food processing plants
 Bakeries/restaurants
 Schools/hospitals
 Pharmaceutical and chemical laboratories
 Industrial lunchrooms/dressing rooms
 Wastewater treatment plants

PRODUCT APPLICATION

SURFACE PREPARATION

NEW, UNCOATED CONCRETE: New concrete should be allowed to cure for a minimum of 30 days before application of any coating. If there is any doubt about the dryness of the concrete, conduct a test by simply placing a weighted rubber mat, plastic sheet or other non-porous material on the surface for 24 hours. Check the underside of the mat and concrete for signs of moisture. The substrate will be darker if damp. If moisture is found, allow additional drying time (10-14 days) and repeat test. If moisture persists, concrete surface cannot be coated.

Remove oil, dirt, grease and other chemical contaminants by cleaning with Krud Kutter® Original Cleaner Degreaser, detergent, or other suitable cleaner. Rinse with water. Etch concrete with Krud Kutter Cleaning & Etching Solution. Rinse thoroughly and immediately, and allow to dry.

RUST-OLEUM®

8100 SYSTEM OVERKRETE® XTRA S

PREMIUM 100% SOLIDS EPOXY FLOOR COATING - SMOOTH

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

Very dense, non-porous or chemically treated concrete may require acid etching, abrasive blasting or sanding to assure proper coating adhesion. Determine porosity by pouring one ounce of water onto the concrete. If water soaks in, the surface is porous enough for coating. If water beads up on the concrete, the surface is not porous and treatment is warranted. The presence of laitance will also require acid etching, abrasive blasting, sanding or grinding to ensure removal per ICRI CSP Level 2.

PREVIOUSLY COATED CONCRETE: Remove loose dirt, dust and paint by sweeping or vacuum cleaning. Remove grease, oil, floor compound or wax as indicated above, in the new, uncoated concrete section. Very glossy or hard coatings should be lightly sanded to insure maximum adhesion. The OverKrete Xtra S will not lift most previous coatings. Concrete floor areas which require patching should be free of dirt, oil, grease and other chemical contaminants as indicated above, in the new, uncoated concrete section. Loose cement and previous paint should also be removed. The 5499 Concrete Patching Compound or 5494 TurboKrete® Concrete Patching Compound can be used to repair damaged areas of the floor. Refer to the product Technical Data Sheet for more information.

MIXING

Hand mixing is not adequate. You must combine the base and activator by power mixing using either a 3" Jiffler Mixer or Hanson Plunge Mixer. Mix at 500-750 rpm for 1-3 minutes. Do not over mix or use higher speeds. This can introduce air into the coating causing small bubbles in the finish.

Start mixing the OverKrete Xtra S part A and immediately add the part B activator. It is very important to transfer as much part B activator as possible, scrape the sides and bottom of the container thoroughly. Mix the two components together for 1-3 minutes being careful to not pull air into the mixture.

Immediately pour the mixture out onto the marked off area of the floor in a long thin stripe. Do not try to work out of the container or put the material in a roller pan as heat will build up and shorten pot life and work time, and could be hazardous. The material on the floor will be workable for about 20 minutes.

NOTE: Do not scrape the sides or bottom of the container. Use only the material that flows naturally out of the container. Also, do not turn the container upside down and leave on the floor to drain. Doing so may result with unactivated material from the sidewall of the container being applied. This will cause soft spots in the coating.

PRODUCT APPLICATION (cont.)

EQUIPMENT RECOMMENDATIONS

SQUEEGEE: Use a high quality rubber squeegee.

ROLLER: Use a high quality short nap (3/8") lint-free roller with a phenolic core such as Rust-Oleum Roller No. 6696.

APPLICATION

Apply only when air and floor temperatures are between 65-90°F. Because of the short pot life, it is recommended the application of the coating be limited to small sections. One activated gallon of OverKrete Xtra S will cover 100 square feet at 16 mils. This can be achieved with a single coat application, however, on bare concrete there is a risk of outgassing from small pinholes, voids and raising temperatures in the concrete during the curing of the coating which will form blisters in the finish.

To greatly reduce the risk of blisters we recommend that bare concrete be first primed with Prime & Seal™ Primer or Penetrating Prime & Seal™ Primer. Refer to the Technical Data Sheet for the primer for more information and application instructions.


NOTE: Outgassing only occurs when there is a rise in temperature causing entrapped air in pinholes to expand. The risk of blisters can also be reduced by avoiding application of the coating during times of the day where temperatures may increase.

After the primer has cured, mark off the floor into 100 square foot sections. Coating this area with one gallon of activated OverKrete Xtra S finish will yield a film thickness of 16 mils. On previously coated floors where outgassing is not a problem, the OverKrete Xtra S can be applied directly to the floor in a single coat application of 16 mils. Mark out the floor into 100 square foot sections for coverage with one gallon of activated material.

After pouring the material onto the floor, use a rubber squeegee to spread the material out over the entire section. Roll the material smooth using a 3/8" nap, lint free roller with a phenolic core. Make all final passes parallel and in the same direction. Do not roll excessively and do not re-roll the material after the final passes are made. Doing so may result in color variations.

NOTE: Change the roller cover every 45-60 minutes and always mount it on the roller frame in the same direction.

After completing the section repeat the process on the adjacent section, overlapping the prior application approximately 6 inches to blend the coating together. Natural breaks in the floor, such as control joints or expansion joints, should be used as stopping points if the entire floor cannot be completed in one day. The coated floor will be ready for foot traffic 12-24 hours after application of the final coat. The coating will be ready for full use in 48-72 hours at 70-80°F and 50% relative humidity. Do not detergent wash the floor for 5 days after application.

RUST-OLEUM®

8100 SYSTEM OVERKRETE® XTRA S

PREMIUM 100% SOLIDS EPOXY FLOOR COATING - SMOOTH

PRODUCT APPLICATION (cont.)

NON-SLIP SURFACES

To obtain a non-slip surface, a two coat application is required. The same basic procedure is followed as for application of the regular high gloss finish. Apply the first coat of OverKrete Xtra S at 16 mils, 1 activated gallon per 100 square foot section, by rubber squeegee and roller. Within 20 minutes after rolling of the first coat, broadcast silica, totally saturating the coated surface. If the floor is being coated in multiple sections, then leave a 12-18 inch area un-sanded along the edge of the section to allow for blending of the coating in the next section.

Use 50 lbs of round particle, 20-40 mesh sand (like Wedron 480) per 100 square foot section. Silica is sold separately. After 4-8 hours, sweep off the excess silica thoroughly. Apply a second coat of OverKrete Xtra S within 12-24 hours at the same spread rate of 16 mils, or 1 gallon per 100 square feet. This second coat anchors the silica and improves the appearance while maintaining the non-slip surface. The floor will be ready for foot traffic in about 12-24 hours after the application of the second coat, and is ready for full use in 48-72 hours. Do not detergent wash for 5 days after application.

THINNING

Not required.

COVERAGE

Smooth finish: 16 mils (400μ)
One coat @ 100 sq. ft. /gal. (2.5 m²/l)

Anti-skid finish: Applied in two coats.* (three steps involved),
45-50 mils (1,125-1,250μ)
1st coat is 100 sq. ft. /gal. (2.5 m²/l) (16 mils (400μ) no less)
Aggregate broadcast while wet

2nd coat* is 100 sq. ft. /gal. (2.5 m²/l)**

*The 2nd coat anchors the aggregate.

** This will vary, based on coarseness of aggregate used.

Equal coverage may be expected when used as a glaze coat over OverKrete HD floor topping.

For special textures or decorative effects, consult application instructions.

SET TIME

Cured adequately for next coating step in 8-10 hours at 70°F (21°C).

CLEAN UP

Xylene can be used to remove material from equipment if it is cleaned before the material has started to set up; otherwise, stronger solvents such as methylene chloride will be necessary.

PRODUCT APPLICATION (cont.)

SAFETY

OverKrete Xtra S contains amine curing agents. Avoid skin contact. In case of eye contact or ingestion, contact a physician immediately. In case of skin sensitivity to these materials, use protective clothing and gloves.

SAFETY DATA SHEETS

Safety Data Sheets are available upon request. It is strongly recommended that they be read by all persons handling OverKrete Xtra S.

If there are any questions on the use of this product, please consult our technical service department.

PERFORMANCE CHARACTERISTICS

COMPRESSIVE STRENGTH

METHOD: ASTM C579

TYPICAL VALUE: 7,900 psi

FLEXURAL STRENGTH

METHOD: ASTM C580

TYPICAL VALUE: 3,700 psi

TENSILE STRENGTH

METHOD: ASTM C307

TYPICAL VALUE: 3,900 psi

TABER ABRASION

METHOD: ASTM 4060, CS 17

TYPICAL VALUE: Loss/1000 cycles = 30 mg.

FILM HARDNESS, SHORE D

METHOD: ASTM D2240

TYPICAL VALUE: 85

EPOXY FLOOR COATING	TECHNICAL DATA	CP-38
	8100 SYSTEM OVERKRETE® XTRA S PREMIUM 100% SOLIDS EPOXY FLOOR COATING - SMOOTH	

PHYSICAL PROPERTIES

8100 SYSTEM OVERKRETE XTRA S		
Resin Type		Polyamine Converted Epoxy
Pigment Type		Varies depending on color
Solvents		Benzyl Alcohol
Weight*	Per Gallon	9.3-9.9 lbs.
	Per Liter	1.11-1.19 kg
Solids*	By Weight	100%
	By Volume	100%
Volatile Organic Compounds*		<100 g/l (0.83 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		High gloss finish: 16 mils Non-slip finish: 16 mils (first coat) (with silica broadcast); 16 mils (second coat)
Wet Film to Achieve DFT		16 mils
Practical Coverage at Recommended DFT		100 square feet per gallon at 16 mils (first coat) 100 square feet per gallon at 16 mils (second coat)
Mixing Ratio		1.7 : 1 base to activator by volume
Induction Period		None
Pot Life @ 70-80°F (21-27°C) & 50% Relative Humidity**		30 minutes
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Foot Traffic	12-24 hours
	Full Use	48-72 hours
	Full Cure	5 days
Shelf Life		5 years
Flash Point		>200°F (93°C)
Safety Information		CAUSES NOSE, THROAT, EYE AND SKIN IRRITATION. CAUSES EYE AND SKIN BURNS. HARMFUL IF SWALLOWED. MAY CAUSE ASTHMA, SKIN SENSITIZATION OR OTHER ALLERGIC RESPONSES. FOR INDUSTRIAL OR COMMERCIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN. SEE THE PRODUCT SAFETY DATA SHEET (SDS) AND LABEL WARNINGS FOR ADDITIONAL SAFETY INFORMATION

*Activated material

**Pot life may be as short as 20 minutes

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 877-385-8155
www.rustoleum.com/industrial

Form: GDH-262
Rev.: 102821