



# TESTORS® CRAFT POURING PAINT SET

## DESCRIPTION AND USES

Testors® Craft Pouring Paint Sets are high quality waterbased paints for general craft use and decorative paint. For use on wood, metal, plastic, and glass. Great for pouring projects or create unique marbling effect.

## PRODUCTS

**3 Color Set** **SKU: 352451**

Set Contents (2oz.)  
Gold, White, and Fuchsia

**3 Color Set** **SKU: 352454**

Set Contents (2 oz.)  
Turquoise, Silver, and Black

## PRODUCT APPLICATION

### SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants. Rinse with fresh water and allow to thoroughly dry.

### APPLICATION

Use at room temperature 70°F (21°C) and humidity is below 60%. Shake paints to ensure fully mixed. Allow to set for several minutes to avoid air bubbles.

Before pouring paint onto the surface, wear gloves for easier clean-up. Simply pour colors directly on surface one color at a time or mix your colors together crating your own color palette. Tilt surface to create a marbled effect. Allow to dry for at least 24 hours.

### CLEAN-UP

Clean brush and other application tools immediately with soap and water.

## PHYSICAL PROPERTIES

		TESTORS CRAFT POURING PAINT SET
<b>Resin</b>		Acrylic WB Emulsion
<b>Pigment</b>		Varies by color
<b>Solids By Weight</b>		30-38%
<b>VOC</b>		<60 g/l
<b>Dry Times at 77°F (25°C) and 50% Relative Humidity</b>	<b>Touch</b>	1-3 hours
	<b>Handle</b>	4-8 hours
	<b>Full Cure</b>	Minimum of 24 hours
<b>Shelf Life</b>		2 Years
<b>Flash Point</b>		>200°F (>93°C)
<b>Safety Information</b>		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.