

• TRUSTED QUALITY SINCE 1921 •



**RUST-OLEUM®
TRUCK BED PLATINUM**

DESCRIPTION AND USES

Rust-Oleum® Platinum Series Truck Bed Coating is built for truck owners that demand long-lasting protection from scratches, impacts, corrosion, and fading.

Rust-Oleum's most advanced and durable truck bed spray contains:

- Specialized Polyurethane technology to provide 5X tougher impact resistance compared to Rust-Oleum's standard truck bed spray
- Stops Rust® formula offers superior protection from rust and corrosion
- High-Output Spray System delivers premium spray experience for even coats and no-drip coverage

For use on: Bare or primed metal truck beds.

PRODUCT

SKU	DESCRIPTION (15 Oz. Aerosol)
382630	Black

PRODUCT APPLICATION

READ ALL DIRECTIONS BEFORE BEGINNING PROJECT

SURFACE PREPARATION

Remove all rust, oil and grease from surfaces to be coated. Surface must be clean and dry. Mask off area to avoid overspray on auto finish. Apply to bare or primed metal surface.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is above 50°F (10°C) and humidity is below 65% to ensure proper drying. Avoid spraying in very windy, dusty conditions. Cover nearby objects to protect from overspray.

Shake can vigorously for one minute after mixing ball begins to rattle. If the mixing ball fails to rattle **DO NOT STRIKE**. Contact Rust-Oleum. Shake often during use. Hold can upright 12-18" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Remove any overspray from the auto finish immediately. For the best results, apply two coats (allow product to dry for 1-2 minutes between coats).

DRY AND RECOAT TIMES

Air dry for a minimum of one hour at 70°F (21°C) – 50% relative humidity. Allow more time at cooler temperatures. Surface can be recoated within 1 hour or after 24 hours. Allow 72 hours for full cure before placing items in the truck bed.

CLEANUP

When finished spraying, wipe off tip before storing. Clean up wet or dry coating with Xylol. Mineral spirits can also be used to remove wet paint. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick a pin or other object into the stem.



**RUST-OLEUM®
 TRUCK BED PLATINUM**

PHYSICAL PROPERTIES

		TRUCK BED PLATINUM
Resin Type		Urethane
Pigment Types		Carbon Black
Solvents		Mixture of Aliphatic, Aromatic and Ketones
Solids	Weight	27.89%
	Volume	15.92%
Fill Weight		15 Oz. (425g)
MIR		0.80 Max
Recommended Dry Film Thickness (DFT) per Coat		1 mil per coat
Practical Coverage at Recommended DFT (assumes 15% material loss)		Up to 30 sq. ft./15 Oz.
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	1 hour
	Handle	2 hours
	Recoat	Before 1 hour and after 24 hours
	Full Cure	7 days
Flash Point		141°F
Shelf Life		5 years.
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

