



TESTORS® COLOR SHIFT SPRAY PAINT

DESCRIPTION AND USES

Testors® Color Shift spray paint projects take on multiple colors at once depending on the light or angle. Color Shift Iridescent Shimmer take on a multi-color rainbow effect depending on the light and angle. Create a color change with as few as 2 coats. Apply additional layers for a different effect. Great for any craft or hobby project.

PRODUCTS

SKU	DESCRIPTION (3 oz. Aerosol)
352455	Turquoise Waters*
352456	Purple Sunrise*
352457	Pink Champagne*
352458	Iridescent Shimmer**

*For best results, apply over black basecoat

**For best results apply over any color basecoat

PRODUCT APPLICATION

Use in a well-ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION

Remove loose paint and rust with wire brush or sandpaper. Lightly sand glossy surfaces. Clean with soap and water, rinse and let dry.

APPLICATION

For best results, apply over recommended basecoat to create a true color change. Try it over other colored basecoats for a dramatic effect. Shake can vigorously before using and re-shake often. Spray can 12"– 14" (31 cm–36 cm) from work. Spray with continuous motion. Apply 2 or more light coats a few minutes apart.

DRY TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Dry to the touch in 20 minutes, dry to handle in 30 minutes, recoat anytime and fully cured in 24 hours.

CLEAN-UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

PHYSICAL PROPERTIES

		COLOR SHIFT
Resin		Acrylic
Pigment		Mica
Solids By Weight		12.36%
Wet Film to Achieve Dry Film Thickness		2-4 mils
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	30 minutes
	Recoat	Anytime
Shelf Life		5 years
Flash Point		-141°F
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.