



PAINTER'S TOUCH® ULTRA COVER SATIN METALLIC FINISH

DESCRIPTION AND USES

Rust-Oleum® Painter's Touch® Satin Metallic Finish provides long lasting protection and durability. This high quality metallic goes on smoothly and provides a rich finish. It is ideal for a variety of indoor projects.

PRODUCTS

SKU	DESCRIPTION (Quart)
254101	Oil-Rubbed Bronze
258203	Aged Copper

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

APPLICATION CONDITIONS

Apply only when air and surface temperatures are above 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with soap and water. Rinse thoroughly with fresh water and allow to fully dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

PRIMING

Use of Painter's Touch Ultra Cover Primer provides a sound base for topcoat adhesion and is especially recommended for bare wood and metal. Recommended primers include 2244T or 267268 White or 1980502 Flat Gray Primer.

APPLICATION

Before using, stir thoroughly to ensure any settled pigment is re-dispersed. If thinning is necessary, thin material only with mineral spirits or acetone. For brush or roller, thin no more than 5%. Apply with a good quality brush, roller, or spray gun. Avoid painting in direct sunlight or on hot surfaces. Avoid excessive brushing as this will reduce film thickness and protection. Use light, even strokes to ensure an even flow and the smoothest finish.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. May recoat when fully dry, usually in 24 hours. Dries to the touch in 2-4 hours and to handle in 5-9 hours.

CLEAN-UP

Clean brush and other application tools with mineral spirits.

	TECHNICAL DATA	PTUC-11
	PAINTER'S TOUCH® ULTRA COVER SATIN METALLIC FINISH	

PHYSICAL PROPERTIES

		ULTRA COVER SATIN METALLIC FINISH
Resin Type		Alkyd
Pigment Type		Varies
Solvents		Hydrotreated Light Distillates, Mineral Spirits
Weight	Per Gallon	7.6-8.5 lbs.
	Per Liter	0.91-1.02 kg
Solids	By Weight	45.8-60.2%
	By Volume	36.4-47.6%
Volatile Organic Compounds		<500 g/l (4.16 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50μ)
Wet Film to Achieve DFT (unthinned material)		2.0-4.0 mils (50-100μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		120 sq. ft./qt. (11.1 m ² /l)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity*	Touch	2-4 hours
	Handle	5-9 hours
	Recoat	Minimum 24 hours
Shelf Life		5 years
Dry Heat Resistance		200°F (93°C)
Flash Point		<105°F (41°C)
Safety Information		See SDS

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 877-385-8155
www.rustoleum.com

Form: ARJ-1980
Rev.: 020420